Stress Corrosion Cracking of High Strength Steels

Eun U. Lee, Henry Sanders and Bhaskar Sarkar
Naval Air Warfare Center Aircraft Division
Patuxent River, Maryland 20670

ABSTRACT

The stress corrosion cracking (SCC) was investigated for AerMet 100 and 300M steels in four aqueous NaCl solutions of different concentrations (0.035-3.5%), three of which had an identical electrical conductivity (12.44×10^{-4} m^2 S mol^{-1}). Especially, the variation of threshold stress intensity for SCC, K_{ISCC}, with cathodic potential was evaluated, employing rising step load test method. The K_{ISCC} increased, peaked at around the potential of -0.7 V_{SCE}, and then decreased with increasing potential for AerMet 100 steel. On the other hand, the K_{ISCC} did not change much with potential for 300M steel. The open circuit potential and the corresponding K_{ISCC} were greater for AerMet 100 steel than for 300M steel, indicating the former nobler and more SCC resistant. The SEM fractographs showed mixed cleavage and intergranular cracking, more cleavage for AerMet 100 steel but more intergranular for 300M steel, at all potentials employed.

INTRODUCTION

Because of its high ultimate tensile strength (UTS), 2,000 MPa, 300M steel had been accepted as the material for aircraft landing gear and other structural components. In 1990, a new steel, AerMet 100, was developed. It has a good combination of high UTS, 1,979 MPa, and high fracture toughness, 126 MPa$\sqrt{m}$, which is much greater than that of 300M steel, 57 MPa$\sqrt{m}$. Consequently, AerMet 100 steel can replace 300M steel to increase damage tolerance. On the one hand, the two steels are susceptible to corrosion, and protective plating is required for service in corrosive environments.

The SCC of AerMet 100 and 300M steels had been investigated rather extensively, employing various test methods: cantilever bend[1], double cantilever beam[2] and rising step load[3]. However, the results had not been quite consistent, as evidenced by different values[1-3] of K_{ISCC}, shown in Table 1. Furthermore, the test environment had been limited to an aqueous 3.5% NaCl solution. Therefore, this study was initiated to identify the effect of NaCl concentration on SCC, and also evaluate and compare the SCC resistance of AerMet 100 and 300M steels in aqueous solutions of different NaCl concentrations.

20000407 140

REPORT DOCUMENTATION PAGE

1. REPORT DATE	2. REPORT TYPE Professional Paper	3. DATES COVERED	
4. TITLE AND SUBTITLE Stress Corrosion Cracking of High Strength Steels		5a. CONTRACT NUMBER	
		5b. GRANT NUMBER	
		5c. PROGRAM ELEMENT NUMBER	
6. AUTHOR(S) Dun u. Lee, Henry Sanders, Bhaskar Sarkar		5d. PROJECT NUMBER	
		5e. TASK NUMBER	
		5f. WORK UNIT NUMBER	

7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) Naval Air Warfare Center Aircraft Division 22347 Cedar Point Road, Unit #6 Patuxent River, Maryland 20670-1161	8. PERFORMING ORGANIZATION REPORT NUMBER
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES) Naval Air Systems Command 47123 Buse Road Unit IPT Patuxent River, Maryland 20670-1547	10. SPONSOR/MONITOR'S ACRONYM(S)
	11. SPONSOR/MONITOR'S REPORT NUMBER(S)

12. DISTRIBUTION/AVAILABILITY STATEMENT

Approved for public release; distribution is unlimited.

13. SUPPLEMENTARY NOTES

14. ABSTRACT

The stress corrosion cracking (SCC) was investigated for AerMet 100 and 300 M steels in four aqueous NaC1 solutions of different concentrations (0.035-3.5%), three of which had an identical electrical conductivity (12.44 x 10^4 m^2 S mol^{-1}). Especially, the variation of threshold stress intensity for SCC, K_{Iscc}, with cathodic potential was evaluated, employing rising step load test method. The K_{Iscc} increased, peaked at around the potential of -0.7 V_{SCE}, and then decreased with increasing potential for AerMet 100 steel. On the other hand, the K_{Iscc} did not change much with potential for 300M steel. The open circuit potential and the corresponding KISCC were greater for AerMet 100 steel than for 300M steel, indicating the former nobler and more SCC resistant. The SEM fractographs showed mixed cleavage and intergranular cracking, more cleavage for AerMet 100 steel but more intergranular for 300M steel, at all potentials employed.

15. SUBJECT TERMS

16. SECURITY CLASSIFICATION OF:			17. LIMITATION OF ABSTRACT	18. NUMBER OF PAGES	19a. NAME OF RESPONSIBLE PERSON Eun Lee / Henry Sanders / Bhaskar Sarkar
a. REPORT	b. ABSTRACT	c. THIS PAGE			19b. TELEPHONE NUMBER (include area code)
Unclassified	Unclassified	Unclassified	Unclassified	16	(301) 342-8069 / 9765 / 8035

Test Method	K_{ISCC} (MPa√m)	
	AerMet	300M
Cantilever Bend[1] (10,000 Hours)	17-24	12-15
Double Cantilever[2] Beam	36	21
Rising Step Load[3] (Opern Circuit Potential)	28	

Table 1. K_{ISCC} in Aqueous 3.5% NaCl Solution

EXPERIMENTAL PROCEDURE

The specimen materials were a forged AerMet 100 steel slab of 2.5 x 10 x 122 cm and a forged 300M steel rod of 13 cm diameter and 51 cm length. Their chemical compositions are shown in Table 2.

Element	AerMet	300M
C	0.23	0.43
Ni	11.12	1.80
Cr	2.99	0.80
Mo	1.17	0.40
Co	13.44	-
Mn	0.01	0.75
Si	0.02	1.60
P	0.002	0.005
S	0.0005	0.005
Fe	balance	balance

Table.2. Chemical Compositions (%) of AerMet 100 and 300M Steels

These steels were subjected to the following heat treatment, respectively.

Steel	Solution Treatment in Vacuum	Quenching in	Freezing	Aging in Vacuum
AerMet	885°C, 1.25 Hr	N_2 Gas	-73°C, 2 Hr	482°C, 5 Hr
300M	871°C, 5 Hr	Oil	-	302°C, 2 Hr (Double)

Table 3. Heat Treatment for AerMet 100 and 300M Steels

The heat treatment resulted in hardness R_c 56 and 53 and microstructures, shown in Figure 1, for the AerMet 100 and 300M steels, respectively. Subsequently, v-notch (60°) square bar specimens of the two steels were machined, Figure 2.

Since the cantilever bend and double cantilever beam tests require a long time, an accelerated test method of rising step load[4] was employed. The specimen was fatigue-precracked to ½ thickness, and then step-loaded in four-point bending under constant displacement control at room temperature, while held at a predetermined potential in a corrosive electrolyte. The load was increased at 2% of the UTS each hour until load drop, which corresponds to crack initiation. A schematic of the rising step loading is shown in Figure 3. The stress intensity factor was calculated as a function of applied bending moment and crack length, using the following equation.

$$K = \sigma\sqrt{\pi a}.F(a/W)$$

where

K: stress intensity factor
σ: gross stress = $6M/bW^2$
M: bending moment = Px
P: applied load
x: moment arm length
b: specimen thickness
W: specimen width
a: crack length
$F(a/W) = 1.122 - 1.40(a/W) + 7.33(a/W)^2 - 13.08(a/W)^3 + 14.0(a/W)^4$

As the corrosive electrolytes, aqueous solutions of four different NaCl and Na_2SO_4 concentrations were used. Three of them had an identical electrical conductivity, 126.44 x $10^{-4}\,m^2\,S\,mol^{-1}$. They were

No.	Aqueous Solution (%)		pH	Electrical Conductivity $10^{-4}\,m^2\,S\,mol^{-1}$
	NaCl	Na_2SO_4		
1	3.5	0.0	7.3	–
2	3.5	2.8	6.3	126.44
3	0.35	6.5	6.1	126.44
4	0.035	6.9	6.1	126.44

Table 4. Aqueous NaCl Solutions of Various Concentrations

Prior to the rising step load test, the open circuit or free corrosion potential was measured for each steel in each solution.

During the test, the specimen was the working electrode in a three-electrode cell with a saturated calomel reference electrode and a platinum counterelectrode. Cathodic potentials, ranging from -1.2 V_{SCE} (volts versus a saturated calomel electrode) to the respective open circuit potential, were applied to generate various amounts of hydrogen in front of the advancing crack tip.

After the SCC test, the fracture surface morphology was examined with a scanning electron microscope (SEM), JEOL JSM-5800LV, operating at a 20 kV accelerating voltage.

RESULTS

1. Open Circuit Potentials

The open circuit potentials (OCP) for the two steels in the four solutions were determined to be

No.	Aqueous Solution (%)		OCP (V_{SCE})	
	NaCl	Na_2SO_4	AerMet	300M
1	3.5	0.0	-0.51	-0.68
2	3.5	2.8	-0.56	-0.70
3	0.35	6.5	-0.61	-0.72
4	0.035	6.9	-0.61	-0.71

Table 5. Open Circuit Potentials

2. Test in Aqueous 3.5% NaCl Solution (No, 1)

The variation of K_{ISCC} with potential is illustrated for the two steels, tested in the aqueous 3.5% NaCl solution (No. 1), in Figure 4. At more negative potentials, the K_{ISCC} values of the two steels tend to close together, and they are 14.2 and 15.9 MPa$\sqrt{m}$ at –1.2 V_{SCE} for the AerMet 100 and 300M steels, respectively. However, with increasing potential, the K_{ISCC} increases, peaks at –0.7 and –0.6 V_{SCE}, and then decreases for AerMet 100 steel. On the other hand, it is relatively constant, 15.9-17.5 MPa$\sqrt{m}$, at all potentials, ranging from –1.2 to -0.68 V_{SCE}, for 300M steel.

The color of electrolyte changed from transparent below -0.8 V_{SCE} to rusty red above -0.8 V_{SCE}, indicating a dissolution reaction, for the both steels.

The K_{ISCC} values at the open circuit potentials, -0.51 and -0.68 V_{SCE}, were found to be 25.6 and 17.5 MPa$\sqrt{m}$ for the AerMet 100 and 300M steels, respectively.

The SEM fractograph of the AerMet 100 steel shows a mixture of more cleavage and interspersed intergranular cracking without any appreciable change across the all potentials employed, Figure 5. Namely, the potential change from -1.2 to -0.51V_{SCE} changes the SCC resistance, K_{ISCC}, but does not change its mode.

The SEM fractograph of the 300M steel shows a mixture of somewhat more intergranular and interspersed cleavage cracking without any noticeable change across the all potentials employed, Figure 6. Compared to the AerMet 100 steel, the 300M steel has larger grains of prior austenite. The constant cracking mode is consistent with the relatively constant values of K_{ISCC} across the all potentials employed.

The K_{ISCC} of the AerMet 100 steel at the open circuit potential in the 3.5% NaCl solution, 25.6 MPa√m, is close to that reported by Buckley[3], 27.5 MPa√m. On the one hand, it is greater than that for the 300M steel, indicating greater SCC resistance for the AerMet 100 steel than for the 300M steel in the solution. Furthermore, it is less than those in the three aqueous solutions of an identical electrical conductivity for the AerMet 100 steel, whereas it is not much different in all of the four solutions for the 300M steel. This indicates that:

- The AerMet 100 steel is less susceptible to SCC in the three aqueous solutions of an identical electrical conductivity than in the 3.5% NaCl solution (No. 1).
- With an identical electrical conductivity, the change in NaCl and Na_2SO_4 concentration from 0.35 to 0.035% does not change the SCC resistance of the AerMet 100 steel.
- With an identical electrical conductivity, the NaCl and Na_2SO_4 concentration does not affect the SCC resistance of the 300M steel.

The SCC mode was found to be a mixture of more cleavage and interspersed intergranular cracking for AerMet 100 steel and the reverse for 300M steel. The cracking mode did not change noticeably across the all potentials employed for the both steels. The more intergranular SCC mode, observable irrespective of potential, demonstrates a weaker link of the prior austenite grain boundaries in the 300M steel than in the AerMet 100 steel.

In their study on PH 13-8 steel, Tyler, Levy and Raymond[6] observed subtle change in the fracture surface morphology of dominant cleavage between the –1.2 and –0.8 V_{SCE} region. On the other hand, they observed clear changes in fracture mode from intergranular (-1.2 V_{SCE}) to cleavage (-0.8 V_{SCE}) for T-250 maraging steel.

CONCLUSIONS

1. The K_{ISCC} increases, peaks at around –0.7 V_{SCE}, and then decreases with increasing potential for AerMet 100 steel in the four solutions of different concentrations. However, it does not change much with potential for 300M steel in those solutions.

2. The open circuit potential and the corresponding K_{ISCC} are

Aqueous Solution (%)		OCP (V_{SCE})		K_{ISCC} (MPa√m)	
NaCl	Na_2SO_4	AerMet	300M	AerMet	300M
3.5	0.0	-0.51	-0.68	25.6	17.5
3.5	2.8	-0.56	-0.70	32.4	16.8
0.35	6.5	-0.61	-0.72	36.8	16.8
0.035	6.9	-0.61	-0.71	36.8	16.8

The above evidences that
- The AerMet 100 steel has greater SCC resistance than the 300M steel in the four aqueous solutions.

- With an identical electrical conductivity, the change in NaCl and Na_2SO_4 concentration from 0.35 to 0.035% does not change the SCC resistance of the AerMet 100 steel.
- With an identical electrical conductivity, the NaCl and Na_2SO_4 concentration does not affect the SCC resistance of the 300M steel.

3. SCC mode is a mixture of cleavage and intergranular cracking, more cleavage for the AerMet 100 steel and more intergranular for the 300M steel, and it is independent of potential.

ACKNOWLEDGMENT

The authors gratefully acknowledge Veena Agarwala for her micrograph preparation and helpful discussion.

REFERENCES

1. J. Kozol and C. E. Neu, "Stress Corrosion Susceptibility of Ultra-High Strength Steels for Naval Aircraft Applications," Report No. NAWCADWAR-92018-60, Naval Air Warfare Center, Aircraft Division Warminster, Warminster, PA, January 1992.

2. Eun U. Lee, "Corrosion Behavior of Landing Gear Steels," Report No. NAWCADWAR-94001-60, Naval Air Warfare Center, Aircraft Division Warminster, Warminster, PA, October 29 1993.

3. P. F. Buckley, R. Brown, J. H. Graves, E. U. Lee, C. E. Neu and J. Kozol, "Corrosion Behavior of High Strength Steels for Aerospace Applications," Proceedings of the 40[th] Sagamore Army Materials Research Conference, 30 Aug.-2 Sept. 1993, Plymouth, MA, pp. 449-464

4. ASM Handbook, Vol. 8, Mechanical Testing, AS M International, June 1995, pp. 539-540.

5. P. Buckley, B. Placzankis, J. Graves and R. Brown, "Stress Corrosion Cracking Performance of AerMet 100 and ESR 4340 Steel as a Function of Potential," Proceedings of the Tri-Service Conference on Corrosion, Plymouth, MA, 12-14 May 1992, pp. 37-45.

6. P. S. Tyler, M. Levy and L. Raymond, "Investigation of the Conditions for Crack Propagation and Arrest under Cathodic Polarization by Rising Step Load Bend Testing," Journal of Science and Engineering Corrosion, February 1991, vol. 47, no. 2, pp.82-87.

(a) AerMet 100 Steel

(b) 300M Steel

Figure 1. Microstructures of Specimen Materials

W = b = 10 mm
a = 5 mm
L = 70 mm

Figure 2. Square Bar Specimen

Figure 3. Schematic of Rising Step Loading

Figure 4. Variation of K_{ISCC} with Potential in Aqueous Solution of 3.5% NaCl

−1.0 V$_{SCE}$

−0.6 V$_{SCE}$

−1.2 V$_{SCE}$

−0.8 V$_{SCE}$

Figure 5. SEM Fractographs of AerMet 100 Steel, SCC Tested in Aqueous 3.5% NaCl Solution

-1.0 V_{SCE}

-0.7 V_{SCE}

-1.2 V_{SCE}

-0.8 V_{SCE}

Figure 6. SEM Fractographs of 300M Steel, SCC Tested in Aqueous
3.5% NaCl Solution

Figure 7. Variation of K_{ISCC} with Potential in Aqueous Solution of 3.5% NaCl and 2.8% Na_2SO_4

Figure 8. Variation of K_{ISCC} with Potential in Aqueous Solution of 0.35% NaCl and 6.5% Na_2SO_4

Figure 9. Variation of K_{ISCC} with Potential in Aqueous Solution of 0.035% NaCl and 6.9% Na_2SO_4